

Library of Congress Preservation Directorate
Specification Number 500-533 – 16
Specifications for Polyester: Poly(ethylene-terephthalate) Jackets
For Card Sleeves for 7", 10", 12", and 16" Audio Discs

This specification is provided as a public service by the Preservation Directorate of the Library of Congress. Any commercial reproduction that implies endorsement of a product, service, or materials, in any publication, is strictly prohibited by law. This Specification is written for L.C. purchasing purposes and is subject to change when necessary. If you are reading a paper copy of this specification please check our website for the most up-to-date version.

1. Composition and Chemical Requirements

1.1 Content

The polyester must be a clear, colorless, [biaxially oriented/stressed/drawn] poly(ethylene-terephthalate), [PET] film.

1.2 Impurities

The clear and colorless PET film must not contain any plasticizer, surface coatings, UV inhibitors, or absorbents, and must be guaranteed to be non-yellowing with natural aging. As received, the film must not contain any coloring agents.

2. Physical and Performance Requirements

2.1 Thickness

The PET film used to construct the jackets must be 3 mil thick.

2.2 Surfaces

The film surface must be free of dents, dings, fingerprints, scratches, abrasions, inclusions or other imperfections.

2.3 Seals

Seals must be done by edge welding unless otherwise specified on the purchase order. All seals must be complete, clear, and continuous. The seals must not be mottled, crystallized, bubbled, brittle, burned, show evidence of capillary marks ("caterpillar tracks"), or other indications of poor seals. Sealed edges must lie flat without causing planar distortion of the item.

2.4 Durability

The sealed edges must be able to withstand moderate handling without separating or splitting. Seals must not crack when tested by pulling the seal between two fingernails at a 45 degree angle. The seal must not separate when tested by running a finger along the inside of the seal. The seal must not split at the beginning of the cut end of the sealed edge when pulled slightly.

3. Product Requirements

3.1 Construction

The enclosure must be constructed of two sheets of PET film of the same size, of equal length on all sides, sealed on three sides. (Illustration below)



Polyester jacket for card sleeves

3.2 Workmanship

The jackets must be cut straight with squared sides. The sizes must be accurate. The edges must be smooth and even and meet exactly.

3.3 Dimensions

The polyester jackets must meet the dimension requirements shown in the table below. These jackets are intended to be used in a two-part preservation housing system consisting of a card sleeve with a polyester jacket that fits over the sleeve. The sleeves and jackets must meet dimension requirements precisely so that the polyester jacket fits easily but not loosely over the card sleeve, without any puckering, binding, or gaping. The dimensions in the following table are minimum outer dimensions. The vendor must ensure that the polyester jackets fit over the card sleeves for the corresponding disc size. The dimensions of the card sleeves, (LC Specification 200-233) are provided here in a separate table, as a reference.

Table 1: Dimensions for Polyester Jackets for Card Sleeves for Audio Discs

Dimensions	7" Disc	10" Disc	12" Disc	16" Disc
Polyester Jacket	7 7/16 x 7 7/16"	10 13/16 x 10 13/16"	12 3/4 x 12 3/4"	16 5/8 x 16 5/8"

Table 2: Reference Table of Card Sleeve Dimensions

Dimensions	7" Disc	10" Disc	12" Disc	16" Disc
Card Sleeve	7 1/4 x 7 1/8"	10 15/32 x 10 5/16"	12 3/8 x 12 1/4"	16 1/4 x 16 1/4"

3.4 Marking

There must be no identification marks on the film.

4. Packaging and Identification

4.1 Inner Packages

Each package must plainly identify the type, size and number of items within, the name of the supplier or manufacturer, year of manufacture, and manufacturing run or batch number.

4.2 Outer Package

The items must be packed in standard commercial containers that are constructed to ensure that they arrive at the Library of Congress in dry, undamaged condition. The outside of each container must be identified by type, size and number of items within; manufacturing run or batch number; LC Purchase Order / Contract number and line number.

5. Compliance with Specification

5.1 Quality Assurance Testing

The Library of Congress has the right to perform any relevant instrumental analyses or tests deemed necessary to ensure that supplies conform to prescribed requirements.

5.2 Sampling

To sample for testing, shipments will be sampled according to ANSI/ASQ Z1.4, inspection level S-2, AQL 2.5%.

5.3 Acceptance

Materials will be accepted when the Library of Congress has ascertained that the products comply with all parts of the specification.

FAILURE TO MEET ANY PART OF THE SPECIFICATION WILL BE CAUSE FOR REJECTION

Configuration Management

Date	Revision History
19-Jun-2002	Initial release of document on website, html format.
14-Dec-2009	Revised and reformatted for release as PDF document.
30-Sept-2016	Editorial update to footer.